



Facile and Green Synthesis of Carboxy Methyl Cellulose Stabilized Bio-Functionalized Gold Nanoparticles and Its Catalytic Activity

K. V. Padmavathi ^{a*}, M. Padma ^b and Nowduri Annapurna ^{b*}

^a Department of Chemistry, GVP College of Degree & PG Courses, Visakhapatnam, India.

^b Department of Engineering Chemistry, AUCE (A), Visakhapatnam, India.

Authors' contributions

This work was carried out in collaboration among all authors. All authors read and approved the final manuscript.

Article Information

DOI: 10.9734/JPRI/2022/v34i28A36023

Open Peer Review History:

This journal follows the Advanced Open Peer Review policy. Identity of the Reviewers, Editor(s) and additional Reviewers, peer review comments, different versions of the manuscript, comments of the editors, etc are available here: <https://www.sdiarticle5.com/review-history/84958>

Received 12 January 2022

Accepted 21 March 2022

Published 30 March 2022

Original Research Article

ABSTRACT

Gold nanoparticles (AuNP's) are synthesized in sustainable green method using Carboxy Methyl Cellulose (CMC) and employed as catalyst in the reduction of p-nitro aniline with NaBH₄ to p-phenylene diamine. It is observed that the speed of reaction was fast due to their size, as particle size decreases surface area increases. It is also observed that the rate of reaction is fast with comparison with the other catalyst. This is because the nanoparticles have more effective surface area and possess less steric hindrance with p-nitro aniline and NaBH₄ when compared to nanoparticles due to their shape. The recyclability of nanoparticles shows it is potential recyclable catalyst for industrial applications.

Keywords: Green synthesis; gold nanoparticles; CM; catalytic reduction; potential recyclable.

1. INTRODUCTION

Noble metal nanoparticles are attracting a great deal of researchers' attention due to their unique properties and perspectives of implementation in

different fields. The areas of application of noble metal nanoparticles are extremely diverse. The possibilities of using noble metal nanoparticles as the agents for targeted delivery of drugs in living organisms, in photodynamic therapy of

*Corresponding author: E-mail: purnaaucevizag@yahoo.co.in;

cancerous tumors, in the treatment of skin diseases, as biocidal disinfectants, as auxiliary materials in the imaging of affected tissues, in catalysis, as well as in other areas are being actively studied. The outstanding susceptibility of noble metal nanoparticles optical spectra to the tiny changes in the surrounding media electrodynamic properties facilitates the development of the chemical and biological sensors on their basis.

Noble metals are used to improve the characteristics of photodetectors and solar panels [1]. Nanostructures of noble metals are actively used as elements for the development of metamaterials [2]. Some efforts have been made to use them in nonlinear optics: for the second harmonic generation [3], for the terahertz radiation generation [4], as well as for studying of the hybrid states, such as plexitons (plasmon-excitons). Nanoparticles of noble metals were used to modify photo-induced changes in molecular layers [5], and also as optical nanoantennas serving to change the rate of radiation processes [6].

Among different noble metal nanoparticles, Gold nanoparticles (AuNP's) have been widely employed in bio-nanotechnology based on their unique properties and multiple surface functionalities. The ease of AuNP's functionalization provides a versatile platform for nano-biological assemblies with oligonucleotides [7] antibodies [8], and proteins [9].

Bio-conjugates of AuNP's have also become promising candidates in the design of novel biomaterials for the investigation of biological systems [10]. The versatility of AuNP's has provided useful materials for a range of biomedical applications. In diagnostics, the binding event between the analytes and the AuNP's can alter the physicochemical properties of AuNP's such as surface plasmon resonance, conductivity, and redox behavior, leading to detectable signals [11]. AuNP's also serve as practical platforms for therapeutic agents, with their high surface area allowing a dense presentation of multifunctional moieties (e.g., drugs [12] and targeting agents [13]). Hence, researchers focused on easy and simple methods to achieve monodispersed and low dimensional nanoparticles. In this context, the present paper describes the synthesis of gold nanoparticles stabilized by CarboxyMethyl Cellulose (CMC) biopolymer and fructose as reducing agents. This method provides an

amicable protocol to produce gold nanoparticles by controlling the size and shape.

2. MATERIALS AND METHODS

Chloroauric acid (HAuCl_4), Fructose and CMC were obtained in pure form Sigma-Aldrich (USA) and are utilized as received without purification. The acquired nanostructures were characterized by means of HR-Transmission Electron Microscope (HR-TEM), X-ray diffraction (XRD) and Fourier Transform Infrared spectroscopy (FT-IR). HR-TEM, selected area electron diffraction pattern (SAED) and energy dispersive x-ray (EDX) data were obtained on an FEI Technai G2 S-Twin. For HR-TEM analysis, a few drops of the Au colloidal samples dispersion onto the carbon coated copper TEM grid and dried overnight. XRD measurements were performed on a Bruker's AXS Model D8 Advance powder x-ray diffractometer instrument operated with $\text{Cu K}\alpha$ radiation as the x-ray source ($\lambda = 1.54 \text{ \AA}$). The FT-IR spectra were collected on the Nicolet 5700 Thermo scientific instrument with the samples as KBr pellets.

2.1 Preparation of Au nanostructures

To synthesize Au nanoparticles, 2 mL of 0.01 M HAuCl_4 aqueous solution was added to the mixture of 2 mL of 1% fructose and 98 mL of 0.1 wt% CMC aqueous solution containing beaker at room temperature. For synthesizing self-assembled Au nanoparticles chain structures, the amount of CMC was 0.5 wt%.

2.2 Catalysis of *p*-Nitroaniline Reduction

p-Nitroaniline of 0.6906 gm and 0.189 gm of NaBH_4 were dissolved in 50 ml of deionized water. Then from this 400 μl of each NaBH_4 and *p*-Nitroaniline solutions were dissolved in 3200 μl of deionized water in volumetric flask. This is the main basic reaction mixture. Taken 1500 μl of this reaction mixture into the cuvette which was dissolved in the 1500 μl of deionized water. To this add 0.05 gm of the prepared nanoparticles as the catalysts to the reaction. Now observe the reaction path of this reaction by using the UV-Visible Spectroscopy.

3. RESULTS AND DISCUSSIONS

The UV-Vis spectrum of the as prepared nanoparticles showed that the characteristic peak 545 nm, which initially attested the formation of low dimensional gold nanoparticles

and it is presented in Fig. 1. Typically, maximum SPR absorption wavelength (λ_m) of GNPs is size and shape. This result motivated us to further characterize the samples in detail.

The characteristic features from HR-TEM confirm the crystallinity of the asprepared Au nanoparticles and the mono-dispersion of Au nanoparticles, as shown in Fig. 2. The EDAX spectrum confirmed the purity and no other particles were presented in the material. These results comply with the previous UV-Vis results, in which the bigger size of particles was formed due to low value of the polarity index of reaction medium that consequent the growth of particles and assembly caused by the highly extended CMC polymer chain in low polarity indexed solvent. However, the Au nanostructures prepared from the use of 0.5% CMC, the spherical nanoparticles with an average

diameter of ~ 15 nm tend to linear assembling and form chain like structures, which was observed in Fig. 2. At high amount of CMC(0.5%), the number of CMC molecules anchoring to the surface of Au particles is increased.

Therefore, the discrete Au nanoparticles directed to assembling in the linear way and form nanoparticle chain like structures via non-covalent interactions formed between the CMC molecules present on the surface of Au particles. The XRD spectrum of the synthesized nanoparticles was presented in Fig. 3. The results showed that the peak at 2θ 28.2 represent the characteristic (111) phase of the fcc structure. The spectra confirmed the formed nanoparticles are in crystalline phase with an average crystalline size of 14.6 nm.





Fig. 1. UV-visible spectra for Gold Nanoparticles






Fig. 2. HR-TEM confirmation of crystallinity of the prepared Au nanoparticles and the mono-dispersion with EDAX spectrum confirm the purity




Fig. 3. XRD spectrum of the synthesized CMC stabilized nanoparticles

The FT-IR spectrum of CMC stabilized Au nanoparticles (Fig. 4) showed some shifts corresponding to stretching vibration of -OH functional group from 3265 to 3420 cm^{-1} , asymmetric stretching vibration of -COO- from 1588 to 1603 cm^{-1} , symmetric stretching vibration of -COO- from 1411 to 1418 cm^{-1} , in-plane vibration of -OH from 1320 to 1331 cm^{-1} and stretching vibration of C-O-C from 1020 to 1060 cm^{-1} . These observations suggest that the prepared Au nanoparticles are stabilized through the interaction of both the -COO- (carboxylate) and -OH (hydroxyl) functional groups in CMC molecules.

4. CATALYTIC STUDIES

Fig. 5 shows the reduction of p-nitroaniline in the presence of gold nanoparticles formed from CMC stabilization was monitored in real time by UV-visible spectroscopy. A blank experiment was carried out for the reduction of p-nitroaniline with NaBH_4 in the absence of gold nanoparticles. There is a very slow decrease in the characteristic absorbance of p-nitroaniline at 378 nm after 24 h. The reaction was performed in the presence of gold nanoparticles where the absorbance peak at 378 nm showed a progressive decrease, a shifting of the

absorbance peak at 223 nm, and the appearance of a new absorption peak at 303 nm. This result indicates that the gold nanoparticles were accelerating the reduction of p-nitroaniline into p-phenylenediamine in the presence of NaBH₄. The reduction rates of this reaction can be considered to be independent of the concentration of NaBH₄ since this reagent was used in large excess with respect to p-nitroaniline. Therefore, this chemical reduction follows first-order kinetics.

Fig. 6 shows the reusable catalytic properties of the metal nanoparticles obtained from use of 0.5% CMC. It is found that, after 6 recycling reactions, the p-Nitroaniline still can be converting to p-phenylenediamine in the presence of NaBH₄ with a conversion rate reaching ~85%. Thus, the metal nanoparticles synthesized are potent recyclable nanocatalyst for the industrial applications.




Fig. 4. FT-IR spectrum of CMC stabilized Au nanoparticles




Fig. 5. Reduction of p-nitroaniline in the presence of gold nanoparticles formed from CMC stabilization




Fig. 6. Recyclability of the Gold nanoparticles obtained as a catalyst for the reduction of p-nitroaniline with NaBH₄

5. CONCLUSION

Gold nanoparticles (AuNP's) were used as an eco-friendly catalyst in a green approach format in water at room temperature to accomplish an efficient chemoselective reduction of p-Nitroaniline. The product of this chemical reduction, p-phenylenediamine, is an attractive intermediate in the preparation of polymers, hair dyes, and rubber products. Hence, there is a great demand to develop efficient catalysts for this chemical reduction of p-nitroanilines. The reactions are worth repeating, since they are reusable and high yielding (around 95 percent).

CONSENT

It is not applicable.

ETHICAL APPROVAL

It is not applicable.

DISCLAIMER

The products used for this research are commonly and predominantly use products in our area of research and country. There is absolutely no conflict of interest between the authors and producers of the products because we do not intend to use these products as an avenue for any litigation but for the advancement of knowledge. Also, the research was not funded by the producing company rather it was funded by personal efforts of the authors.

COMPETING INTERESTS

Authors have declared that no competing interests exist.

REFERENCES

- Castelletto S, Boretti A. Noble Metal Nanoparticles in Thin Film Solar Cells. *Nanoscience and Nanotechnology Letters*. 2013;5(1):36–40. DOI:10.1166/nnl.2013.1396
- Noble Metal Nanostructure Synthesis at the Liquid–Substrate Interface: New Structures, New Insights, and New Possibilities, Svetlana Neretina, Robert A. Hughes, Kyle D. Gilroy, and Maryam Hajfathalian *Accounts of Chemical Research*. 2016;49(10):2243-2250. DOI: 10.1021/acs.accounts.6b00393
- Timbrell D, You JW, Kivshar YS. et al. A comparative analysis of surface and bulk contributions to second-harmonic generation in centrosymmetric nanoparticles. *Sci Rep*. 2018;8:3586. Available:https://doi.org/10.1038/s41598-018-21850-8
- Takano K, Asai M, Kato K. et al. Terahertz emission from gold nanorods irradiated by ultrashort laser pulses of different wavelengths. *Sci Rep*. 2019;9:3280. Available:https://doi.org/10.1038/s41598-019-39604-5
- Liang, Hongyan, Wei, Hong, Pan, Deng and Xu, Hongxing. "Chemically synthesized noble metal nanostructures for

- plasmonics" *Nanotechnology Reviews*. 2015;4(3):289-302. Available: <https://doi.org/10.1515/ntrev-2014-0026>
6. Nikita Toropov, Tigran Vartanyan, Noble Metal Nanoparticles: Synthesis and Optical Properties☆, *Comprehensive Nanoscience and Nanotechnology* (Second Edition), Academic Press. 2019:61-88. ISBN 9780128122969, 10.1016/B978-0-12-803581-8.00585-3.
 7. (a) Zhang T, Chen P, Sun Y, Xing Y, Yang Y, Dong Y, Xu L, Yang Z, Liu D. *Chem. Commun.* 2011;47:5774–5776. [PubMed] [Google Scholar](b) Guo S, Huang Y, Jiang Q, Sun Y, Deng L, Liang Z, Du Q, Xing J, Zhao Y, Wang PC, Dong A, Liang X-J. *ACS Nano*. 2010;4:5505–5511. [PMC free article] [PubMed] [Google Scholar](c) Park S, Hamad-Schifferli K. *ACS Nano*. 2010;4:2555–2560. [PMC free article] [PubMed] [Google Scholar]
 8. (a) Mukherjee P, Bhattacharya R, Bone N, Lee YK, Patra CR, Wang S, Lu L, Secreto C, Banerjee PC, Yaszemski MJ, Kay NE, Mukhopadhyay D. *J. Nanobiotech.* 2007;5:4. [PMC free article] [PubMed] [Google Scholar](b) Eck W, Craig G, Sigdel A, Ritter G, Old LJ, Tang L, Brennan MF, Allen PJ, Mason MD. *ACS Nano*. 2008;2:2263–2272. [PubMed] [Google Scholar](c) El-Sayed IH, Huang XH, El-Sayed MA. *Nano Lett.* 2005;5:829–834. [PubMed] [Google Scholar]
 9. (a) Calzolari L, Franchini F, Gilliland D, Rossi F. *Nano Lett.* 2010;10:3101–3105. [PubMed] [Google Scholar](b) You C-C, Arvizo RR, Rotello VM. *Chem. Commun.* 2006;42:2905–2907. [PubMed] [Google Scholar](c) Aubin-Tam ME, Hamad-Schifferli K. *Langmuir*. 2005;21:12080–12084. [PubMed] [Google Scholar]
 10. (a) Moyano DF, Rotello VM. *Langmuir*. 2011 Article ASAP. [PMC free article] [PubMed] [Google Scholar](b) Jamison JA, 1, Bryant EL, Kadali SB, Wong MS, Colvin VL, Matthews KS, Calabretta MK. *J. Nanoparticle Research*. 2011;13:625–636. [Google Scholar](c) You CC, Chompoosor A, Rotello VM. *Nano Today*. 2007;2:34–43. [Google Scholar]
 11. (a) Uehara N. *Anal. Sci.* 2010;26:1219–1228. [PubMed] [Google Scholar](b) Wang Z, Ma L. *Coord. Chem. Rev.* 2009;253:1607–1618. [Google Scholar](b) Radwan SH, Azzazy HME. *Expert. Rev. Mol. Diagn.* 2009;9:511–524. [PubMed] [Google Scholar](c) Baptista P, Pereira E, Eaton P, Doria G, Miranda A, Gomes I, Quaresma P, Franco R. *Anal. Bioanal. Chem.* 2008;391:943–950. [PubMed] [Google Scholar]
 12. (a) Brown SD, Nativo P, Smith J-A, Stirling D, Edwards PR, Venugopal B, J. Flint D, Plumb JA, Graham D, Wheate NJ. *J. Am. Chem. Soc.* 2010;132:4678–4684. [PMC free article] [PubMed] [Google Scholar](b) Alexander CM, Maye MM, Dabrowiak JC. *Chem. Commun.* 2011;47:3418–3420. [PubMed] [Google Scholar](c) Cheng Y, Samia AC, Li J, Kenney ME, Resnick A, Burda C. *Langmuir*. 2010;26:2248–2255. [PubMed] [Google Scholar](d) Duncan B, Kim C, Rotello VM. *J. Control. Release*. 2010;148:122–127. [PMC free article] [PubMed] [Google Scholar]
 13. (a) Khan JA, Kudgus RA, Szabolcs A, Dutta S, Wang E, Cao S, Curran GL, Shah V, Curley S, Mukhopadhyay D, Robertson JD, Bhattacharya R, Mukherjee P. *Plos One*. 2011;6:e20347. [PMC free article] [PubMed] [Google Scholar](b) Patra CR, Bhattacharya R, Wang E, Katarya A, Lau JS, Dutta S, Mudders M, Wang S, Buhrow SA, Safgren SL, Yaszemski MJ, Reid JM, Ames MM, Mukherjee P, Mukhopadhyay D. *Cancer Research*. 2008;68:1970–1978. [PubMed] [Google Scholar]

© 2022 Padmavathi et al.; This is an Open Access article distributed under the terms of the Creative Commons Attribution License (<http://creativecommons.org/licenses/by/4.0>), which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

Peer-review history:
 The peer review history for this paper can be accessed here:
<https://www.sdiarticle5.com/review-history/84958>